

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
18 January 2001 (18.01.2001)

PCT

(10) International Publication Number  
**WO 01/04205 A1**

(51) International Patent Classification<sup>7</sup>: C08K 9/04.  
C09C 1/42, 3/10

[DE/DE]; Schuppenhoernlestrasse 48, D-79868 Feldberg-Falkau (DE). MÜLHAUPT, Rolf [DE/DE]; Ferdinand Kopf-Strasse 9, D-79117 Freiburg (DE). FINTER, Jürgen [DE/DE]; Erwinstrasse 64, D-79102 Freiburg (DE).

(21) International Application Number: PCT/EP00/06422

(22) International Filing Date: 6 July 2000 (06.07.2000)

(74) Common Representative: VANTICO AG; Patents/Scientific Information, Klybeckstrasse 200, CH-4057 Basel (CH).

(25) Filing Language: English

(26) Publication Language: English

(81) Designated State (*national*): US.

(30) Priority Data:  
1288/99 13 July 1999 (13.07.1999) CH

(84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

(71) Applicant (*for all designated States except US*): VANTICO AG [CH/CH]; Klybeckstrasse 200, CH-4057 Basel (CH).

Published:  
— With international search report.

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): ZILG, Carsten

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: NANOCOMPOSITES

(57) Abstract: A composition comprising (A) a resin mixture consisting of (A1) from 0.5 to 50.0 % by weight, based on the sum of components A1 + A2, of an epoxidised or maleinated natural or synthetic oil, and (A2) from 50.0 to 99.5 % by weight, based on the sum of components A1 + A2, of a polymerisable or curable monomer or monomer mixture other than A1, and (B) an organophilic layer silicate obtainable by treatment of a natural or synthetic layer silicate with a swelling agent selected from sulfonium, phosphonium and ammonium compounds, but in the case where component A1 is an epoxidised oil, salts of melamine compounds and cyclic amidine compounds are excluded as ammonium compounds, is suitable for the preparation of nanocomposites having a high degree of toughness and tensile strength.

WO 01/04205 A1

2001011801001

